

Morland's Euroclass B fire retardant Formica faced panels are tested to EN13501 using 15mm Medite MDF bonded with a Formica 0.7mm HPL face.

Applications For Interior Use:

- FR Wall Panels For Public Areas
- FR Partitions
- FR Ceiling Panels
- FR Access Panels

Benefits:

- Comforms With Approved Document B
- Attractive Finish
- Easy To Install



Specification Details EN13501 Class B S1 D0

Fire Resistant Core Thickness (mm)	15	18	22
Dimensions (mm)	2440x1220 or 3050x1220		
Tolerance- Thickness (mm)	EN324-1 (+/- 0.3)		
Tolerance- Dimensions (mm)- UNCUT PANELS ONLY	EN324-1 (+/- 3mm)		
Tolerance- Edge Damage (mm)- UNCUT PANELS ONLY	10		
Tolerance- Perimeter Registration- UNCUT PANELS ONLY	-/+ 5mm		
Average Density	800KG per/m3 (+/- 10%) (15mm)		
Core Manufactured Standard	EN622-5		
Core Property	FR-MDF		
Formaldehyde Release	Class E1		
Moisture Content	EN322 (5-9%)		
Certification	FSC® - Available on request		
EUTR Status	Compliant- Sourced within the EU		
CE Marked	No		
Material Safety Data Sheet	Available On Request		

Additional Features

Quality Feature	Unit	Result	Standard
Resistance to dry heat	Rating	4	EN 438-2:2005
Resistance to water	Rating	3	EN 438-2:2005
Resistance to staining	Rating	4	EN 438-2:2005
Light fastness (Xenon)	Grey scale	4-5	EN 438-2:2005
Resistance to Cigarette	Rating	3	EN 438-2:2005

Characteristics:

Fire Resistant Medium Density Fibreboard (FR-MDF) provides a tough, smooth surface with no imperfections which provides an ideal surface for many commercial applications.

Morland fire retardant panels are bonded on both faces with either a matching or balancing Formica laminate to ensure stability and FR approval.

Laminate (Decor) Type	Laminate (Decor) Thickness	Applications
High Pressure Laminate (HPL)	0.7mm	FR Wall Panels For Public Areas, FR Partitions, FR Ceiling Panels, FR Access Panels

Machining

Because decorative laminates have a relatively hard surface, tool wear will be greater. For longer life and better performance tungsten carbide tipped (TCT) saws and cutters should be used. For specific information please visit our website (www.morland-uk.com).

Edge Finishing

Moisture ingress may cause the panel to swell and result in internal/ external de-lamination. We strongly recommend that all edges are sealed.

Cleaning

Due to the resistant and hygienic, dense surface, Laminate does not require any special form of care. The laminate surfaces consists of melamine resin impregnated decor paper and the surfaces are generally easy to clean. This also applies to textured surfaces. There is no need to use any care products. Furniture polishes and cleaning agents that contain wax should not be used as they have a tendency to clog up the surface structure of laminates and to form a sticky layer that attracts dirt. Laminate surfaces should be cleaned regularly. When cleaning is necessary, mild agents should be used. Cleaning agents must in particular not contain any abrasive components, as they may adversely affect the gloss level or scratch the surface. As many kinds of soiling can occur, from slight and fresh to heavy and obstinate, and a huge range of different substances may be involved, it is essential to use the correct cleaning procedure.

Maintenance

As a general rule spilled substances such as tea, coffee and wine etc. should be cleaned immediately as the cleaning effort increases if they are left to dry. → The following instructions should be observed in daily use:

Placing burning cigarettes on the laminate surface leads to surface damage. Always use an ashtray.

Laminate surfaces should not be used as a cutting surface as this can also leave cutting marks on highly resistant laminate surfaces. **Always use a chopping board.**

Placing hot cooking utensils such as saucepans and frying pans directly from the hob or oven onto the laminate surface should be avoided, as, depending on the heat exposure, a change in the gloss appearance or damage to the surface can arise. **Always use heat resistant mats.**

Spilled liquids should always be cleaned up immediately, especially in the areas around cut-outs and joints as prolonged exposure to some substances may cause a change in the gloss appearance of the laminate surface.